

TX7

ULTRA RAPID CURING CERAMIC EPOXY WEARING COMPOUND



DATA SHEET

Ultra-fast curing compound, 100% solids, ceramic-filled with a special reinforcement matrix containing aramid fibers for greater resistance to abrasion and impact. Good chemical resistance in the presence of caustics and acids. Easily applied with a trowel, spatula, or by hand using latex gloves.

- Perfect for quick repairs and patching.
- Extreme adhesion to steel, bronze, aluminum, and concrete
- Protection against corrosion and abrasion

APPLICATION AREAS

- Chutes
- Hoppers
- Cyclones
- Wear plates
- Centrifugal pumps
- Pipe elbows
- Hydro pulpers
- Ash separators
- Impellers
- Coal crushers
- Screw conveyors

COVERAGE

10 kg kit covers 1.67m² (18 sf)
3 mm thickness (120 mils)

COLOR

Blue

PACKAGING

Size	Reorder #	Size	Reorder #	Size	Reorder #	Size	Reorder #
1 kg	TX7-01	2 kg	TX7-02	10 kg	TX7-10	20 kg	TX7-20

TECHNICAL DATA

Maximum Temperature (depending on the service)	Wet Service Dry Service	70°C 93°C	158°F 200°F
Flexural Strength	(ASTM D 790)	526 kg/cm ² (51.5 MPa)	7,470 psi
Pull-off Adhesion	(ASTM D 4541)	242 kg/cm ² (23.7 MPa)	3,430 psi
Tensile Strength	(ASTM D 638)	234 kg/cm ² (22.9 MPa)	3,322 psi
Shore D Hardness	(ASTM D 2240)	85	
Taber Abrasion CS-10, 1000g, 1000 Cycles	(ASTM D 4060)	17mg	
Pot Life	25 min / kg at 72°F		
SAG Vertical Resistance at 21°C (70°F) and 6 mm (240mils)	No sagging		
Mixing Ratio	2:1 by Weight	Base: Activator	
Shelf Life (unopened containers)	3 years at 55-95°F (13-35°C)		



Taurus Epoxy, Inc.
12481 NW 44th. Coral Springs FL 33065 USA
Tel: (561) 757 – 5620
E-mail: taurus@taurusepoxy.com
Website: www.taurusepoxy.com



SURFACE PREPARATION

Proper surface preparation is essential for the long-term performance of this product. The exact requirements for surface preparation vary depending on the severity of the application, the expected service life, and the initial condition of the substrate. All sharp edges and welds must be ground to a 3mm (120 mil) radius using an abrasive disc. Optimal preparation will provide a thoroughly cleaned surface, free of all contaminants, and roughened to an angular profile between 75–125µm (3–5 mil). This is typically achieved through initial cleaning and degreasing, followed by abrasive blasting to near-white metal cleanliness, or by mechanical preparation.

MIX

Mix the activator well in the base with the mixing rod scraping the sides and the bottom of the container. Mix by weight 2 parts Base to 1 part of Activator. Mix thoroughly to produce a uniform and without stripes. Never put solvents.

APPLICATION

Use a heavy-duty plastic brush or a putty knife to apply a minimum thickness of 3mm. Work the material into the substrate profile to achieve maximum adhesion and eliminate any trapped air. Shape the contour using a putty knife or plastic applicator. If a mold or form is used, make sure to coat its surface with a release agent to prevent the material from sticking.

APPLICATION TEMPERATURE

Keep between 55 and 95°F (17 to 35°C). Substrate: Keep between 45 and 105°F (7 to 40°C). The temperature difference of the substrate and material should never exceed 10°F (5°C). The substrate shall be at least 5°F (3°C) above the dew point. Do not apply if the relative humidity exceeds 90%. If necessary, heat the metal before surface preparation using electric heater or heat lamp. Never use gas, oil or kerosene heaters, as they will leave a greasy residue on the metal surface. For best results, keep all material in the warm zone overnight (75°F+) for easy mixing.



CURED TIME

	16°C (60°F)	25°C (77°F)	32°C (90°F)
Tack Free	25 min	20 min	13 min
Light Load	30 min	25 min	20 min
Recoat Time	30 min	25 min	20 min
Full Load	40 min	30 min	25 min

CLEAN

Tools should be thoroughly cleaned immediately after use with a strong alkaline detergent.

SAFETY

Before using any product, review the Safety Data Sheet (SDS) or Safety Data Sheet for your area. Follow standard confined space entry and work procedures, if applicable.

Manufacturer, Taurus Epoxy Inc., makes no warranty either expressed or implied including warranties of merchantability or fitness for a particular purpose for this product. Under no circumstances will the manufacturer be liable for incidental, consequential, or other damages, breach of warranty, strict liability, or any other theory arising out of use of this product. The information and/or recommendations contained herein are based on standard Product and are proprietary and furnished solely for the use of our customers. This information is provided in good faith and believed to be true and accurate as of the date/version of this document. As the manufacturer has no control over the use conditions or application process of the parties using this product, the manufacturer cannot accept responsibility for loss, injury or other damages resulting from the use of the Product or this or any other information provided by the manufacturer. Therefore, no guarantees of any kind, expressed or implied, are made by the manufacturer, Taurus Epoxy Inc., regarding this, or any, product manufactured by them or any contracted or licensed manufacturer. Taurus epoxy products do not provide structural integrity or improvement. They are only used to provide protection from corrosion, wear, abrasion and chemical attack on a given substrate and only to the extent provided for in the Data Sheets, Technical Data Sheets, Safety Data Sheets, and any other information as supplied in writing directly from manufacturers technical support.

